

TECHNICAL REFERENCE 401-BMCLT

BENTOMAT® CLT CERTIFIED PROPERTIES


MATERIAL PROPERTY	TEST METHOD	TEST FREQUENCY	REQUIRED VALUES
Bentonite Swell Index ¹	ASTM D 5890	1 per 50 tonnes	24 mL/2g min.
Bentonite Fluid Loss ¹	ASTM D 5891	1 per 50 tonnes	18 mL max.
Bentonite Mass/Area ²	ASTM D 5993	40,000 ft ² (4,000 m ²)	0.75 lb/ft ² (3.6 kg/m ²) min.
GCL Tensile Strength ³	ASTM D 6768	200,000 ft ² (20,000 m ²)	45 lbs/in (70 N/cm) MARV
GCL Peel Strength ³	ASTM D 6496	40,000 ft ² (4,000 m ²)	3.5 lbs/in (6.1 N/cm) min.
GCL Index Flux ⁴	ASTM D 5887	Periodic	1 X 10 ⁻⁹ m ³ /m ² /sec max.
GCL Hydraulic Conductivity ⁴	ASTM D 5887	Periodic	5 X 10 ⁻¹⁰ cm/sec max.
GCL Hydrated Internal Shear Strength ⁵	ASTM D 5321 ASTM D 6243	Periodic	500 psf (24 kPa) typical

Bentomat CLT is a reinforced GCL consisting of a layer of sodium bentonite between two geotextiles, which are needlepunched together and laminated to a 20-mil (0.5mm) textured HDPE geomembrane.

Notes

- Bentonite property tests performed at a bentonite processing facility before shipment to CETCO's GCL production facilities.
- Bentonite mass/area reported at 0 percent moisture content.
- All tensile strength testing is performed in the machine direction using ASTM D 6768. All peel strength testing is performed using ASTM D 6496. Upon request, tensile and peel results can be reported per modified ASTM D 4632 using 4 inch grips.
- ASTM D5887 Index flux and hydraulic conductivity testing with deaired distilled/deionized water at 80 psi (551 kPa) cell pressure, 77 psi (531 kPa) headwater pressure and 75 psi (517 kPa) tailwater pressure. Reported value is equivalent to 92 gal/acre/day. This flux value is equivalent to a permeability of 5x10⁻¹⁰ cm/sec for typical GCL thickness. ASTM D 5887 testing is performed only on a periodic basis because the membrane is essentially impermeable.
- Peak value measured at 200 psf (10 kPa) normal stress for a specimen hydrated for 48 hours. Site-specific materials, GCL products, and test conditions must be used to verify internal and interface strength of the proposed design.

Distributed by: Bowman Construction Supply, 10801 E. 54th Avenue, Denver, CO 80239;
Phone: (303)696-8960



LAST UPDATED MAY 2007

IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.CETCO.com. CETCO accepts no responsibility for the results obtained through application of this product. CETCO reserves the right to update information without notice.

CETCO®

www.CETCO.com

2870 Forbs Avenue Hoffman Estates, IL 60192
847.851.1800 | 800.527.9948