

TECHNICAL REFERENCE 401-BM600CL

BENTOMAT® 600 CL CERTIFIED PROPERTIES

Distributed by:

Quick Supply Co.
www.quicksupplydm.com
(515)289-1271

MATERIAL PROPERTY	TEST METHOD	TEST FREQUENCY	REQUIRED VALUES
Bentonite Swell Index ¹	ASTM D 5890	1 per 50 tonnes	24 mL/2g min.
Bentonite Fluid Loss ¹	ASTM D 5891	1 per 50 tonnes	18 mL max.
Bentonite Mass/Area ²	ASTM D 5993	40,000 ft ² (4,000 m ²)	0.75 lb/ft ² (3.6 kg/m ²) min.
GCL Tensile Strength ³	ASTM D 6768	200,000 ft ² (20,000 m ²)	30 lbs/in (53 N/cm) MARV
GCL Peel Strength ³	ASTM D 6496	40,000 ft ² (4,000 m ²)	1 lb/in (1.75 N/cm) min.
GCL Index Flux ⁴	ASTM D 5887	Periodic	1 X 10 ⁻⁹ m ³ /m ² /sec max.
GCL Hydraulic Conductivity ⁴	ASTM D 5887	Periodic	5 X 10 ⁻¹⁰ cm/sec max.
GCL Hydrated Internal Shear Strength ⁵	ASTM D 5321 ASTM D 6243	Periodic	150 psf (7.2 kPa) typical

Bentomat 600CL is a needle-punched GCL consisting of a layer of sodium bentonite between woven and nonwoven geotextiles, which are needlepunched together and laminated to a thin flexible membrane liner.

Notes

- 1 Bentonite property tests performed at a bentonite processing facility before shipment to CETCO's GCL production facilities.
- 2 Bentonite mass/area reported at 0 percent moisture content.
- 3 All tensile strength testing is performed in the machine direction using ASTM D 6768. All peel strength testing is performed using ASTM D 6496. Upon request, tensile and peel results can be reported per modified ASTM D 4632 using 4 inch grips.
- 4 Index flux and permeability testing with deaired distilled/deionized water at 80 psi (551kPa) cell pressure, 77 psi (531 kPa) headwater pressure and 75 psi (517 kPa) tailwater pressure. Actual flux values vary with field condition pressures.
- 5 Peak value measured at 200 psf (10 kPa) normal stress for a specimen hydrated for 48 hours. Site-specific materials, GCL products, and test conditions must be used to verify internal and interface strength of the proposed design.

LAST UPDATED JULY 2009

IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.CETCO.com. CETCO accepts no responsibility for the results obtained through application of this product. CETCO reserves the right to update information without notice.

CETCO®

www.CETCO.com

2870 Forbs Avenue Hoffman Estates, IL 60192
847.851.1800 | 800.527.9948